CONDUCTIVE COATING
KUS CC4482

VOC: 604 g/l or less, 5.04 lb/gl
Meets Air Quality Regulations

KUS CC4482 CONDUCTIVE COATING has excellent adhesion over wood and metal with conductivity less than 8 Mega Ohms.

Product Number: KUS CC4482-GL Gray

CONDUCTIVE COATING
KUS CC4482

DIRECTIONS FOR USE

Mix thoroughly before application.

SURFACE PREPARATION

Prior to application, the surface must be dry, clean and free from wax, grease, oil, rust, dirt or any other foreign matter.

Use a compliant surface cleaner in regulated areas. Sand and featheredge original finish with 220 or 320 wet or dry sandpaper. Use a pretreatment coating over bare metal for additional corrosion protection.

THINNING

NO REDUCTION REQUIRED.

APPLICATION

Apply 2 wet coats. Wait approximately 10 to 15 minutes for flash time, then follow with another wet coat if needed.

AIR-DRY (77°F)

Dust-free: 20 to 30 minutes.

PRODUCT USAGE

NOTE: FOR USE BY PROFESSIONAL, TRAINED PERSONNEL, USING PROPER EQUIPMENT WITH STANDARD SAFETY PROCEDURES. NOT INTENDED FOR SALE TO THE GENERAL PUBLIC. FOR PROFESSIONAL USE ONLY. NOT FOR RESIDENTIAL USE.

REFER TO THE PRODUCT LABEL AND MATERIAL SAFETY DATA SHEET (MSDS) FOR CAUTIONS AND WARNINGS PERTAINING TO THIS PRODUCT.

EQUIPMENT CLEANING

Clean spray guns and coating application equipment in an enclosed equipment cleaner. Use KT-025 Compliant Cleaning Solvent. Follow your local air quality regulations for solvent VOC requirements.

TECHNICAL DATA)

VOC:	604 g/l or less, 5.04 lb/gl
Color:	GL Gray
Finish:	Flat
Solvent:	Nickel, Methyl Ethyl Ketone, Alcohol, Methyl Isobutyl Ketone, Naphtha, 2-Heptanone and Methyl Amyl Ketone
Flash Point:	1°F TCC
Dry-to-Touch:	Less than 30 minutes
% Solids by Volume:	25%
% Solids by Weight:	56%
Coverage:	400 sq. ft. per gallon @ 1 mil DFT
Viscosity:	85 KU
Recoat Time:	10-15 minutes
Shelf Life:	1 year from date of manufacture when stored at temperatures not to exceed 90°F

10/14