

PRODUCT PROFILE SHEET




Quality Automotive Products
Established 1974

www.CustomShopPaint.com

EUROPEAN HIGH PERFORMANCE URETHANE CLEAR KUS LVG-2363 MOD

VOC: 250 g/l or less, 2.08 lb/gl (Combined Components)

Meets Air Quality Regulations



EUROPEAN HIGH PERFORMANCE URETHANE CLEAR is formulated for premium productivity. This two-component polyurethane system with a 2:1 ratio offers a durable, fast dry finish. This product is user-friendly, resulting in increased production.

Product Number: KUS LVG-2363 MOD

PRODUCT PROFILE SHEET



Quality Automotive Products
Established 1974

www.CustomShopPaint.com

EUROPEAN HIGH PERFORMANCE URETHANE CLEAR KUS LVG-2363 MOD

SURFACE PREPARATION GENERAL

Prior to application, the surface must be dry, clean and free from wax, grease, oil, rust, dirt or any other foreign matter.

Use KW-901 GREASE AND WAX REMOVER to clean surface. Sand and featheredge original finish with 220 or 320 wet or dry sandpaper.

DIRECTIONS FOR USE

IMPORTANT! To be mixed only with KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CLEAR PART A and KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CATALYST PART B. Before mixing KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CLEAR PART A and KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CATALYST PART B, read the cautions and warnings on both labels. Any mixture containing KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CLEAR PART A and KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CATALYST PART B will have the hazards of BOTH components. OBSERVE ALL APPLICABLE PRECAUTIONS.

MIXING

MIX ONLY WHEN READY TO SPRAY! Mix ratio is 2 parts KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CLEAR PART A with 1 part KUS LVG-2363 MOD EUROPEAN HIGH PERFORMANCE URETHANE CATALYST PART B. MIX ONLY ENOUGH MATERIAL TO SPRAY TWO (2) WET COATS. Viscosity of the mixed product as supplied is approximately 18 to 20 seconds in a #2 Zahn cup at 77°F.

POT LIFE

Pot life of the mixed components is approximately 5 hours at 77°F. The pot life will shorten at a higher temperature.

THINNING

NO REDUCTION REQUIRED.

PRODUCT USAGE



NOTE: FOR USE BY PROFESSIONAL, TRAINED PERSONNEL, USING PROPER EQUIPMENT WITH STANDARD SAFETY PROCEDURES. NOT INTENDED FOR SALE TO THE GENERAL PUBLIC. FOR PROFESSIONAL USE ONLY. NOT FOR RESIDENTIAL USE.

REFER TO THE PRODUCT LABEL AND MATERIAL SAFETY DATA SHEET (MSDS) FOR CAUTIONS AND WARNINGS PERTAINING TO THIS PRODUCT.

DRY TIME

AIR-DRY (77°F):

Dust-free	20-30 minutes
Hard dry:	Overnight
Full cure:	7 days
Force dry:	Flash-off time – 15 minutes
	Dry time – 20 minutes @ 140°F

EQUIPMENT CLEANING

Clean spray guns and coating application equipment in an enclosed equipment cleaner. Use KT-025 Compliant Cleaning Solvent. Follow your local air quality regulations for solvent VOC requirements.

TECHNICAL DATA (Combined Components)

VOC:	250 g/l or less, 2.08 lb/gl
Color:	Clear
Finish:	Gloss
Solvent:	Ketones, Parachlorobenzotrifluoride, Glycol Ether, Methyl Acetate, N-Pentyl Propionate, Xylene, Ethylbenzene and Benzene
Flash Point:	1°F TCC
Dry-to-Touch:	Less than 2 hours
% Solids by Volume:	43%
% Solids by Weight:	45%
Coverage:	690 sq. ft. per gallon @ 1 mil DFT
Viscosity:	18-20 seconds in #2 Zahn cup @ 77°F
Recoat Time:	2 hours
Shelf Life:	1 year from date of manufacture when stored at temperatures not to exceed 90°F