

Instrument Color Coat KUS NIT-ALL COLOR

VOC: 707 g/l or less, 5.9 lb/gal



Custom Shop Nitrocellulose Color is a durable coating formulated to produce a high quality color finish with excellent hardness and cold check resistance.

EQUIPMENT CLEANING:

Clean spray guns and coating application equipment in an enclosed equipment cleaner. Use KT-025 Compliant Cleaning Solvent. Follow your local air quality regulations for solvent VOC requirements.

SURFACE PREPARATION:

Prior to application, the surface must be dry, clean and free from wax, grease, oil, rust, dirt or any other foreign matter. Use KT-025 Compliant Cleaning Solvent on unpainted surfaces. Sand and feather-edge original finish with 220 or 320 wet or dry sandpaper.


THINNING:

No thinning is required.

DRY TIMES:

Surface Dry	30 minutes
Full Cure	Overnight

PRODUCT USAGE:



NOTE: FOR USE BY PROFESSIONAL, TRAINED PERSONNEL, USING PROPER EQUIPMENT WITH STANDARD SAFETY PROCEDURES. NOT INTENDED FOR SALE TO THE GENERAL PUBLIC. FOR PROFESSIONAL USE ONLY. NOT FOR RESIDENTIAL USE. REFER TO THE PRODUCT LABEL AND MATERIAL SAFETY DATA SHEET (MSDS) FOR CAUTIONS AND WARNINGS PERTAINING TO THIS PRODUCT.

TECHNICAL DATA:

VOC: _____ 707 g/l or less, 5.9 lb/gal
 Color: _____ Various
 Finish: _____ Gloss
 Solvent: _____ Di (2-ethylhexyl) Phthalate, Methyl Isobutyl Ketone, Toluene, Ethylbenzene and Methyl Isobutyl.
 Flash Point: _____ 1°F TCC
 Dry-to-Touch: _____ Less than 30 minutes
 % Solids by Volume: _____ 19%
 % Solids by Weight: _____ 27%
 Coverage: _____ 310 sq. ft. per gallon @ 1 mil DFT
 Viscosity: _____ 20 seconds (+/- 4 seconds) in #2 Zahn cup @77°F
 Recoat Time: _____ 30 minutes
 Shelf Life: _____ 1 year from date of manufacture when stored at temperatures not to exceed 90°F